

Painting Procedure

PAINTING	Surface preparation	Primer coat	Intermediate undercoat	Finish coat	Total dry film thickness (DFT)	Colour shade
Main tank, pipes, conservator tank, oil storage tank & DM Box etc. (external surfaces)	Shot Blast cleaning Sa 2 ½*	Epoxy base Zinc primer (30-40µm)	Epoxy high build Micaceous iron oxide (HB MIO) (75µm)	Aliphatic polyurethane (PU) (Minimum 50µm)	Minimum 155µm	RAL 7035
Main tank, pipes (above 80 NB), conservator tank, oil storage tank & DM Box etc. (Internal surfaces)	Shot Blast cleaning Sa 2 ½*	Hot oil proof, low viscosity varnish or Hot oil resistant, non-corrosive Paint	--	--	Minimum 30µm	Glossy white for paint
Radiator (external surfaces)	Chemical / Shot Blast cleaning Sa 2 ½*	Epoxy base Zinc primer (30-40µm)	Epoxy base Zinc primer (30-40µm)	PU paint (Minimum 50µm)	Minimum 100µm	Matching shade of tank/ different shade aesthetically matching to tank
contractor may also offer Radiators with hot dip galvanised in place of painting with minimum thickness of 40µm (min)						
Radiator and pipes up to 80 NB (Internal surfaces)	Chemical cleaning, if required	Hot oil proof, low viscosity varnish or Hot oil resistant, non-corrosive Paint	--	--	--	--
Digital RTCC Panel	Seven tank process as per IS:3618 & IS:6005	Zinc chromate primer (two coats)	--	EPOXY paint with PU top coat or POWDER coated	Minimum 80µm / for powder coated minimum 100µm	RAL 7035 shade for exterior and Glossy white for interior
Control cabinet / Marshalling Box - No painting is required.						

Note: (*) indicates Sa 2 ½ as per Swedish Standard SIS 055900 of ISO 8501 Part-1.

Unused inhibited Insulating Oil Parameters

Sl. No.	Property	Test Method	Limits
A Function			
1a.	Viscosity at 100degC	ISO 3104 or ASTM D445 or ASTM D7042	(Max.) 3 mm ² /s
1b.	Viscosity at 40degC	ISO 3104 or ASTM D445 or ASTM D7042	(Max.)12 mm ² /s
1c.	Viscosity at -30degC	ISO 3104 or ASTM D445 or ASTM D7042	(Max.)1800 mm ² /s
2.	Appearance	A representative sample of the oil shall be examined in a 100 mm thick layer, at ambient temperature	The oil shall be clear and bright, transparent and free from suspended matter or sediment
3.	Pour point	ISO 3016 or ASTM D97	(Max.)- 40degC
4.	Water content a) for bulk supply b) for delivery in drums	IEC 60814 or ASTM D1533	(Max.) 30 mg/kg 40 mg/kg
5.	Electric strength (breakdown voltage)	IEC 60156 or ASTM D1298	(Min.)50 kV(new unfiltered oil) / 70 kV (after treatment)
6.	Density at 20 deg C	ISO 3675 or ISO 12185 or ASTM D 4052	0.820 - 0.895 g/ml
7.	Dielectric dissipation factor (tan delta) at 90 deg C	IEC 60247 or IEC 61620 Or ASTM D924	(Max) 0.0025
8.	Negative impulse testing KVp @ 25 deg C	ASTM D-3300	145 (Min.)
9.	Carbon type composition (% of Aromatic, Paraffins and Naphthenic compounds)	IEC 60590 or ASTM D 2140	Max. Aromatic : 4 to12 % Paraffins : <50% & balance shall be Naphthenic compounds.
B Refining/Stability			
1.	Acidity	IEC 62021-1 or ASTM D974	(Max) 0.01 mg KOH/g
2.	Interfacial tension at 27degC	ISO 6295 or ASTM D971	(Min) 0.04 N/m
3.	Total sulphur content	BS 2000 part 373 or ISO 14596 or ASTM D129	0.15 % (Max.)
4.	Corrosive sulphur	IEC 62535	Non-Corrosive on copper and paper
		ASTM D1275B	Non-Corrosive
5.	Presence of oxidation inhibitor	IEC 60666 or ASTM D2668 or D4768	0.08% (Min.) to 0.4% (Max.) Oil should contain no other additives .Supplier should declare presence of additives, if any.

6.	2-Furfural content	IEC 61198 or ASTM D5837	25 Microgram/litre (Max.)
C Performance			
1	Oxidation stability -Total acidity -Sludge - Dielectric dissipation factor (tan delta) at 90degC	IEC 61125 (method c) Test duration 500 hour IEC 60247	Max 0.3 mg KOH/g Max 0.05 % Max 0.05
2.	Oxidation stability (Rotating Bomb test)	IEC : 61125(Method B) / ASTM D2112 (e)	220 Minutes (Min.)
D Health, safety and environment (HSE)			
1.	Flash point	ISO 2719	(Min.)135degC
2.	PCA content	BS 2000 Part 346	Max 3%
3.	PCB content	IEC 61619 or ASTM D4059	Not detectable (Less than 2 mg/kg)
E Oil used (inhibited) for first filling, testing and impregnation of active parts at manufacturer's works shall be same type of oil which shall be supplied at site and shall meet parameters as mentioned below:			
1	Break Down voltage (BDV)		70kV (min.)
2	Moisture content		5 ppm (max.)
3	Tan-delta at 90°C		0.005 (max)
4	Interfacial tension		0.04 N/m (min)
F Each lot of the processed oil shall be tested prior to filling in main tank at site for the following:			
1	Break Down voltage (BDV)		70 kV (min.)
2	Moisture content		5 ppm (max.)
3	Tan-delta at 90°C		0.0025 (Max)
4	Interfacial tension		More than 0.04 N/m
G After filtration & settling and prior to energisation at site oil shall be tested for following:			
1	Break Down voltage (BDV)	IS: 1866 / IEC 60422	70 kV (min.)
2	Moisture content at hot condition		5 ppm (max.)
3	Tan-delta at 90°C		0.005 (Max)
4	Interfacial tension		More than 0.04 N/m
5	*Oxidation Stability	Test method as per IEC 61125 method C, Test duration: 500hour for inhibited oil	
	a) Acidity		0.3 (mg KOH /g) (max.)
	b) Sludge		0.05 % (max.)
	c) Tan delta at 90 °C		0.05 (max.)
6	*Total PCB content		Not detectable (less than 2 mg/kg total)
* Separate oil sample shall be taken and test results shall be submitted within 45 days after commissioning for approval of KSEBL.			